

Thermal Interface Material

Thermally Conductive High Voltage Insulative Pad

**MATERIAL**

Silicone rubber reinforced with fiberglass, filled with functional ceramic particles

**FEATURES**

- Provides lowest thermal resistance with the highest dielectric strength
- Resistant to tears and punctures
- Sheet stock or cut to specification

PROPERTIES	TEST METHOD	GP-IP1025	GP-IP1035	GP-IP1050
Softness	ASTM D2240	70 Shore A		
Thermal Impedance @ 50 psi	ASTM D5470 Modified	0.64 °C-in ² /W	0.79 °C-in ² /W	0.90 °C-in ² /W
@ 345KPa		4.12 °C-cm ² /W	5.10 °C-cm ² /W	5.78 °C-cm ² /W
Thermal Conductivity	ASTM D5470	1.0 W/m-K		
Thickness		0.25mm	0.35mm	0.50mm
Standard Sheet Sizes		230mmX400mm (individual die-cut shapes available)		
Pressure Sensitive Adhesive		Single-sided PSA with "A1" suffix; double-sided PSA with "A2" suffix		
Tensile Strength	ASTM D638	110 psi		
Volume Resistivity	ASTM D257	>8X10 ¹⁴ Ohm-cm		
Thermal Expansion		150 ppm/°C		
Breakdown Voltage	ASTM D149	>9000 VAC	>14000 VAC	>18000 VAC
Dielectric Constant @ 1MHz	ASTM D257	3.2		
Operating Temperature	TGA+DMA	-55 to 200 °C		
Flammability Rating	UL 94	94V-0		
Density		2.2 g/cc		
Composition		Fiberglass Reinforced Silicone Rubber		
Color		Blue		

GET IN TOUCH

[EMAIL: SUPPORT@TENNMAX.COM](mailto:SUPPORT@TENNMAX.COM)
[TEL: +1 360-567-0707](tel:+13605670707)

TENNMAX.COM

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery. V1